


SOLAR INNOVA GREEN TECHNOLOGY, S.L. N.I.F.: ESB-54.627.278 Paseo de los Molinos, 12, Bajo 03660 - NOVELDA (Alicante) SPAIN Tel./Fax: +34 965075767 E-mail: info@solarinnova.net Website: www.solarinnova.net



### PHOTOVOLTAIC SOLAR ENERGY SOLAR GLASS PAVEMENT - SI-ESF-M-BIPV-RD-M156-28-145W





Solar Innova uses the latest materials to manufacture photovoltaic solar pavement.

Our solar pavement is ideal for any application that uses the photoelectric effect as a clean energy source because of its minimal chemical pollution and no noise pollution. Thanks to its design, can be integrated easily into any installation.

The front of the solar pavement contains a tempered solar glass anti-slip with high transmissivity, low reflectivity and low iron content.

This PV solar pavement use high-efficiency monocrystalline silicon cells to transform the energy of sunlight into electric energy. Each cell is electrically rated to optimize the behavior of the module.

The cell circuit is laminated using PVB (Polyvinyl Butyral) as an encapsulant which provides complete protection and seals against environmental agents and electrical insulation.

The rear of the solar pavement contains a tempered solar glass low iron content.

with symmetric lengths of cable, with a diameter of copper section of 4 mm and an extremely low contact resistance, all

designed to achieve the minimum voltage drop losses.

Our solar pavement complies with all safety requirements not only flexibility but also double insulation and high resistance to UV rays, all are suitable for use in outdoor applications. The design of this solar pavement makes its integration in both industrial and residential buildings (one of the most emerging sectors in the photovoltaic market), and other infrastructure, simple and aesthetic.

#### WARRANTIES

Our manufacturing plants have been prepared in accordance with the ISO 9001, ISO 14001 and OHSAS 18001.

We have quality control divided into three elements:

- $\sqrt{\text{Regular inspections allow us to guarantee the quality of the raw material.}}$
- $\sqrt{1}$  Quality control in the process of our manufacturing procedures.
- $\sqrt{}$  Quality control of finished products, we conduct through inspections and tests of reliability and performance.

Our solar PV pavement is certified by internationally recognized laboratories and are proof of our strict adherence to international safety standards, long term performance and overall quality of products.



Air quality: 1.5



# PHOTOVOLTAIC SOLAR ENERGY SOLAR GLASS PAVEMENT - SI-ESF-M-BIPV-RD-M156-28-145W

	TRICAL CHARACTERISTICS (S	
Maximum power (Pmpp)	Wp	145
Tolerance	Wp	0 ~ + 5
Voltage at maximum power (Vmpp)	Volts	17.25
Current at maximum power (Impp)	Amperes	9.59
Open circuit voltage (Voc)	Volts	20.41
Short circuit current (Isc)	Amperes	10.19
Maximum system Voltage (Vsyst)	Volts	1,000 (IEC)
Diodes (By-pass)	Quantity	2
Maximum series fuse	Amperes	20
Efficiency (ηm)	%	12.74
Form Factor	%	≥ 73

 STC:
 Irradiance: 1,000 W/m<sup>2</sup>
 Module temperature: 25° C

ELECTRICAL CHARACTERISTICS (TONC)					
Maximum power (Pmpp) Wp 107					
Volts	15.70				
Amperes	7.79				
Volts	18.65				
Amperes	8.26				
	Wp       Volts       Amperes       Volts				

NOCT: Irradiance: 800 W/m <sup>2</sup>	Air temperature: 20° C	Air quality: 1.5	e Wind speed: 1 m/s
--	------------------------	------------------	---------------------

MECHANICAL CHARACTERISTICS				
Size	Height	1,437 mm		
	Width	792 mm		
	Thickness	21 mm		
Weight	Net	49 kg		
Front	Material	High transmission tempered glass anti-slip		
	Thickness	8 ± 0.2 mm		
Cells	Туре	Monocrystalline		
	Quantity	4 x 7		
	Size	156 x 156 mm		
Serial connection	Quantity	28		
Parallel connection	Quantity	1		
Encapsulation	Material	PVB		
	Thickness	0.76 ± 0.03 mm		
Rear	Material	Tempered glass		
	Thickness	8 ± 0.2 mm		
Junction box	Material	PVC		
	Protection	IP65		
	Isolation	Versus humidity and inclement weather		
Cables	Туре	Polarized and symmetric in length		
	Length	650 mm		
	Section	4 mm <sup>2</sup>		
	Feetunee	Low contact resistance		
	Features	Minimal losses for voltage drop		
Connectors	Material	PVC		
	Туре	MC4		
	Protection	IP67		

THERMAL CHARACTERISTICS				
Temperature coefficient of short circuit current a (Icc)	%/º C	+ 0.0814		
Temperature coefficient of open circuit voltage $\beta$ (Voc)	%/º C	- 0.3910		
Temperature coefficient of maximum power γ (Pmpp)	%/º C	- 0.5141		
Temperature coefficient of current at maximum power (Impp)	%/º C	+ 0.10		
Temperature coefficient of voltage at maximum power (Vmpp)	%/º C	- 0.38		
NOCT (Nominal Operating Cell Temperature)	° C	+ 47 ± 2		





# PHOTOVOLTAIC SOLAR ENERGY SOLAR GLASS PAVEMENT - SI-ESF-M-BIPV-RD-M156-28-145W

OPTICAL CHARACTERISTICS					
Transmitance	%			35	
	TOLERANCES				
Working temperature		° C	٩F	- 40 ~ + 85	- 40 ~ + 185
Dielectric Isolation Voltage		Volts	5	3,000	
Relative humidity		% 0~100			
Wind resistance		m/s 60			
		kg/m <sup>2</sup>	Pa	245	2,400
		lbs/fee	et²	491.56	
Mechanical load-bearing capacity		kg/m <sup>2</sup>	Pa	551	5,400 (IEC)
		lbs/feet <sup>2</sup>	Pa	75.2	3,600 (UL)
Fire resistance		Clase	5	A (UL 790)	
Wind resistance		Clase	9	F (ASTM D310	51)
Hail resistance		Leve		4 (ANSI FM 4	473)

MEASUREMENTS PERFORMED IN ACCORDANCE WITH STANDARD TEST METHODS					
EN 60904-3 AND ASTM E1036, CORRECTED TO STANDARD TEST CONDITIONS (STC)					
Air quality/Spectral distribution AM 1.5 ASTM G173-03e1 (2,008)					
Luminous intensity/Radiation W/m <sup>2</sup> 1,000					
Cell temperature ° C 25					

MEASUREMENTS PERFORMED IN SOLAR SIMULATOR				
Class AAA (according to IEC 60904-4)				
Power measurement uncertainty is within ± 3 %				
Power measurement uncertainty is within $\pm 3\%$				

STRUCTURAL CHARACTERISTICS		
Cells	High efficiency cells with anti-reflective layer of Silicon Nitride.	
Electric conductors	Flat Copper (Cu) bath in a Tin (Sn) and Silver (Ag) alloy, which improves weldability.	
Welding	Of cells and drivers in sections for stress relief.	
Laminate	Composed of ultra-clear tempered glass on the front, thermostable, PVB encapsulant embedding cells and electrical insulation on the rear formed by a tempered glass.	
Junction box	Hoses and quick connectors with anti-error. Include bypass diodes, interchangeables thanks to the wiring system has no welds, all electrical contacts are made by pressure, thus avoiding the possibility of cold welding.	

#### CHARACTERISTICS OF WORK

- The power of solar cells varies in the output of the production process. The different power specifications of these modules reflect this dispersion.

- Cells during the early months of light exposure, may experience a degradation photonics could decrease the value of the maximum power of the module up to 3%.

- The cells, in normal, operating conditions, reach a temperature above the standard measurement conditions of the laboratory. The NOCT is a quantitative measure of the increase. NOCT measurement is performed under the following conditions: radiation of  $0.8 \text{ kW/m}^2$ , temperature 20° C and wind speed of 1 m/s.

- The electrical data reflects typical values of the modules and laminates as measured at the output terminals at the end of the manufacturing process.

WARRANTIES				
Manufacturing defects	Years	12		
Performance	Minimal Rated Power	90 % at 10 years,		
	%/Years	80 % at 25 years.		


CERTIFICATES					
ISO	CE				



SOLAR INNOVA GREEN TECHNOLOGY, S.L. N.I.F.: ESB-54.627.278 Paseo de los Molinos, 12, Bajo 03660 - NOVELDA (Alicante) SPAIN Tel./Fax: +34 965075767 E-mail: info@solarinnova.net Website: www.solarinnova.net



### PHOTOVOLTAIC SOLAR ENERGY SOLAR GLASS PAVEMENT - SI-ESF-M-BIPV-RD-M156-28-145W



The specifications and technical data may be subject to possible modifications without notice. This data sheet are conform to the requirements of the Standard EN 50380:2003.



SOLAR INNOVA GREEN TECHNOLOGY, S.L. N.I.F.: ESB-54.627.278 Paseo de los Molinos, 12, Bajo 03660 - NOVELDA (Alicante) SPAIN Tel./Fax: +34 965075767 E-mail: info@solarinnova.net Website: www.solarinnova.net



## PHOTOVOLTAIC SOLAR ENERGY SOLAR GLASS PAVEMENT - SI-ESF-M-BIPV-RD-M156-28-145W

### PERFORMANCE

